450°F SUPER FLEXIBLE EPOXY So Flexible You Can Tie it in a Knot

450°F - DURALCO[™] 4538

Now, unlike ever before, there is a solution for applications requiring the ultimate in thermal shock and vibration resistance, sound absorption and excellent adhesion to dissimilar substrates.

Duralco $^{\scriptscriptstyle\rm M}$ 4538 offers the flexibility of silicones and the chemical stability of epoxies.

This completely variable system can be tailored to meet any application requirement just by varying the mix ratio of resin to hardener resulting in the exact degree of flexibility required for any application.

It's easy to use. Just dispense resin and hardener, mix to a uniform color and apply.

Adheres to most plastics, metals, ceramics, glass, rubber and even Teflon $^{\text{\tiny TM}}$ (treated).

Cures at room temperature for use from -100° F to $+450^{\circ}$ F and will not soften or gum up at high temperatures.

Duralco $^{\scriptscriptstyle\rm TM}$ 4538 offers excellent chemical resistance and high bond and peel strength.

It is ideal for all electric and electronics applications and can be used with most common chemicals and solvents.

Users Report:

Bonds: Zytel[™]101, Victrex[™], Poly-Phenylsulfone, Nylon, Poly-Carbonates, Phenolics and other difficult materials. Successfully bonds a Teflon[™] housing to a Ceramic Bushing, Ceramic magnets to a plastics holder.

Thermal Shock Resistance: Withstands repeated thermal cycling from -100°F to +300°F.

Seals: Bonded and sealed a 4 inch diameter glass sight port to a brass housing for use from -100° F to $+300^{\circ}$ F.

Encapsulates: Stress free potting of delicate electronic assemblies for severe thermal shock environments.

High Peel Strength: Adheres to TeflonTM (treated) and other hard to bond plastics.

Duralco^m 4538's convenient room temperature cure and superior high temperature performance makes it easy to use in any prototype or production application.

Adjusting the Flexibility

Just pick the degree of flexibility desired.

Then select the resin to hardener ratio from the table.

- Use formulation "A" for applications where additional rigidity is required.
- Use formulation "B" for most applications.
- Use formulation "C" or "D" for severe thermal shock, vibration or bonding of dissimilar materials that require additional flexibility.



So Flexible You Can Tie it in a Knot Great for Stress Free Bonding & Encapsulating

Duralco ™	4538	
Maximum Temperature	450°F	
Components - Color	2-Tan	
Mixed Viscosity (cps)	17,200	
Mixed Density (gm/cc)	1	
Hardness Variable (Shore A)	60-80	
Tensile Strength (psi)	6,000	
Thermal Conductivity (BTU-in/Hr. Ft ² °F)	7	
Thermal Expansion (10 ⁻⁵ /°C)	N/A	
Dielectric Strength (volts/mil.)	450	
Volume Resistivity (ohm-cm)	10 ¹⁴	
Elongation (%)	8	
Thermal Stability (% 1000 hr @ 200°C)	0.5	
Shrinkage (% max.)	0.8	
Moisture Absorption (% 30 Days)	0.5	
Mix Ratio (R/H)	100:120	
Cure Hr. @ R.T.	16 - 24	
@ 250°F (min.)	60	

Α	В	С	D
Rigid	Flexible	Soft	Softest
100	100	100	100
80	120	200	300
Α	В	С	D
100	60	40	30
100 8000	60 6000	40 2500	30 1200
	A Rigid 100 80 A	A B Rigid Flexible 100 100 80 120 A B	A B C Rigid Flexible Soft 100 100 100 80 120 200 A B C

Availability:

Cat. No.	Description	Temp.
Duralco 4538-1A	1⁄2 Pint	450°F
Duralco 4538-1	Pint Kit	450°F
Duralco 4538-2	Gallon Kit	450°F

Pre-Measured Kits

Each Unit Contains: 1 jar of resin, 1 syringe of hardener and 1 mixing stick. (See page 19 for details) (Ration 100 Resin to 120 Hardener unless otherwise specified)

EE4538-10...... 10 Epox-Eez 10gm units/box EE4538-25...... 10 Epox-Eez 25gm units/box For Epox-EEZ Twin Pack Cartridges (See Page 18.)

